

PR30BZP Etch Primer

TECHNICAL DATA SHEET

Product Description

PR30BZP is a two pack chromated etch primer, suitable for use as a pretreatment primer coat. PR30BZP promotes excellent adhesion between epoxy and polyurethane primers and a variety of light alloys and steel.

- Alternative pretreatment to chemical conversion coatings
- Good corrosion resistance
- Phenolic modified for excellent water resistance
- Used to reactivate aged anodized or chromated surfaces
- REACH authorized for aerospace use

Components



Mix Ratio (by volume)

- | | |
|-----------------------------------|----------|
| • PR30BZP (Base) | 1 part |
| • TH34B (Acid Catalyst) | 1 part |
| • T105 (Thinner) anti chill
OR | 0.1 part |
| • T112 (Thinner) general use | 0.1 part |

Specifications



PR30BZP meets the requirements of:

- BS2X32 A & B

Product Compatibility

PR30BZP is compatible with the following primer specifications:

- BS2X33A+B
- Def Stan 80-206
- Def Stan 80-207

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Surface Preparation and Pretreatment



Ensure the surface is clean, dry and intact using a high performance solvent cleaner - DeSoto® CN20 or Desoclean™ 45 solvent cleaner are recommended.

PR30BZP Etch Primer

Instructions for Use



Ensure all mixing and measuring containers to be used are clean. Stir the base component thoroughly to fully incorporate any slight settlement. Mix base with acid catalyst then add thinner as required. When mixed PR30BZP is ready for use once induction period has been observed.

Note: All products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.




Induction Time:

15-30 minutes



Viscosity: (23°C/73°F)

Apply as mixed



Pot Life:

4 hours @ 15-35°C (59-95°F)

Application Guidelines

Recommended Application Conditions:

Temperature	15 - 35°C (59 - 95°F)
Relative Humidity	30 - 85%

Application:

Apply a light wet closed film to achieve a dry film thickness of 4 - 8 µm. The applied coating should be an iridescent yellow / golden colour.



Note: Over application / excessive film build of product will result in a dark brown discolouration of the dry film.




Theoretical Coverage: (ready for use)

11 m² /Lt @ 6 µm dry film thickness
440 ft/US gal @ 0.24 mil dry film thickness

Recommended Dry Film Thickness:

4 - 8 µm
0.16 - 0.32 mil

PR30BZP Etch Primer



Dry Film Density:

1.6 g/cm³
13 lbs./US gal

Dry Film Weight:

10 g/m² @ 6 µm dry film thickness
0.002 lbs/ft² @ 0.24 mil dry film thickness

Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.

Equipment:

PR30BZP is compatible with most types of current spray equipment, but is NOT suitable for application with electrostatic spray equipment.



Equipment Type	Tip Size	Pressure
Airmix	9 to 11 thou	44 to 73 psi (3 to 5 bar)
HVLP Air Spray	1.2 to 1.6 mm	
Conventional Air Spray	1.2 to 2.2 mm	
Airless	9 to 11 thou	1450 to 1885 psi (100 to 130 bar)
Air-assisted Electrostatic	Not Recommended	
Low Pressure Electrostatic	Not Recommended	

Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto® CN20, CN44 or Desoclean™ 45 solvent cleaners are recommended.

Physical Properties



Colour:

Yellow



Gloss:

≤ 20 units with a 60° gloss meter

PR30BZP Etch Primer



DRYING TIMES @ 23°C (73°F) 75% R.H.	
Dry to Touch	20 minutes
Dry to Handle	45 minutes
Dry to Overcoat	1 to 24 hours
Dry to Mask	2 hours
Full Cure	7 days

Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.

Force Drying:

PR30BZP should not be force dried at temperatures above 60°C (140°F) unless already overcoated with another product.



VOC: (ASTM)

Mixed ready for use	770 g/Lt
PR30BZP Base Component	710 g/Lt
TH34B Acid Catalyst	810 g/Lt
T105 Thinner	940 g/Lt
T112 Thinner	800 g/Lt



Flash Point:

PR30BZP Base Component	-4°C (25°F)
TH34B Acid Catalyst	-4°C (25°F)
T105 Thinner	40°C (104°F)
T112 Thinner	-5°C (23°F)

Shelf Life:

PR30BZP Base Component	24 months in original unopened container
TH34B Acid Catalyst	24 months in original unopened container
T105 & T112 Thinners	10 years in original unopened container

Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

PR30BZP Etch Primer

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.



PR30BZP Etch Primer

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC - South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Desoclean and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace
Sealants and Coatings
Darlington Road
Shildon, Co Durham UK
DL4 2QP

www.ppgaerospace.com

Issue Date: 05/18

Lit: 4593